



Material - AS/NZS 1565 935B

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group - Non-Ferrous Copper Alloy

Sub Group - AS/NZS 1565 Copper and Copper Alloys - Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.	As-Cast	
Iron	Fe %	0.200 max.		
Nickel	Ni %	1.000 max.		
Phosphorus	P %	0.050 max.		
Lead	Pb %	8.000 - 10.000		
Sulphur	S %	0.080 max.		
Antimony	Sb %	0.300 max.		
Tin	Sn %	4.300 - 6.000		
Zinc	Zn %	2.000 max.		
Copper	Cu %	83.000 - 86.000		
-	-	-	Mechanical Properties Tensile Strength in Mpa 160 - 230 Yield Strength in Mpa 60 - 130 Elongation in % 5 - 9 Reduction of Area in % - Hardness in HB 45 - 60 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LB4	BS	British	Casting
C93500	AS	Australia	Ingot and Casting
CuPb9Sn5	ISO	International	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.