



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - AS/NZS 1565 952C

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group - Non-Ferrous Copper Alloy

Sub Group - AS/NZS 1565 Copper and Copper Alloys - Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	8.500 - 9.500	As-Cast	
Iron	Fe %	2.500 - 4.000		
Magnesium	Mg %	0.050 max.		
Manganese	Mn %	1.000 max.		
Lead	Pb %	0.050 max.		
Silicon	Si %	0.250 max.		
Tin	Sn %	0.100 max.		
Zinc	Zn %	0.500 max.		
Copper	Cu %	86.000 min.		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	520 min.
-	-	-	Yield Strength in Mpa	210 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AB1	BS	British	Casting
C95210	AS	Australia	Ingot and Casting
CuAl10Fe3	ISO	International	Rod and Bar
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS