

## Material - AS/NZS 1568 365

## Standard Specification for Copper and Copper-Alloy Forgings

Group - Non-Ferrous Copper Alloy

Sub Group - AS/NZS 1568 Copper and Copper-Alloy Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Forging

Chemical Composition			Heat Treatment	
Iron	Fe %	0.150 max.		
Lead	Pb %	0.250 - 0.700		
Tin	Sn %	0.250 max.		
Copper	Cu %	58.000 - 61.000	Normalizing or Annealing or Tempering	g or Tempering
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	310 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
B171 C36500	ASTM	USA	Plate and Sheet	
B283 C36500	ASTM	USA	Forging	
SB-171 C36500	ASME	USA	Plate and Sheet	
SB-283 C36500	ASME	USA	Forging	
C36500	AS	Australia	Forging	
C36500	UNS	USA	Rod, Bar and Shapes	
B124 C36500	ASTM	USA	Rod, Bar and Shapes	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## ONE STOP SOLUTION FOR METAL PARTS