



Material - ASME SA-494 CX2MW

Standard Specification for Castings, Nickel and Nickel Alloy

Group - Non-Ferrous Nickel Alloys

Sub Group - ASME SA-494 CX2MW Castings, Nickel and Nickel Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.800 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	20.000 - 22.500		
Tungsten	W %	2.500 - 3.500		
Molybdenum	Mo %	12.500 - 14.500		
Vanadium	V %	0.350 max.		
Iron	Fe %	2.000 - 6.000		
Nickel	Ni %	Balance	Mechanical Properties Tensile Strength in Mpa 550 min. Yield Strength in Mpa 310 min. Elongation in % 30 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A 494 CX2MW	ASTM	USA	Casting
C-NiCr21Mo14Fe4W3	AFNOR NF	France	Casting
NC6022	AFNOR NF	France	Casting
N26002	UNS	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.