



## Material - ASME SB-150 C61300

### Specification for Aluminum Bronze Rod, Bar and Shapes

Group - Non-Ferrous Copper Alloy

Sub Group - ASME SB-150 Aluminum Bronze Rod, Bar and Shape

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar and Shapes

Chemical Composition			Heat Treatment	
Aluminium	Al %	6.000 - 7.500	As Drawn or Stress Relieving	
Cadmium	Cd %	0.050 max.		
Chromium	Cr %	0.050 max.		
Iron	Fe %	2.000 - 3.000		
Manganese	Mn %	0.200 max.		
Ni + Co	Ni% + Co%	0.150 max.		
Phosphorus	P %	0.015 max.		
Lead	Pb %	0.010 max.		
Silicon	Si %	0.100 max.		
Tin	Sn %	0.200 - 0.500		
Zinc	Zn %	0.100 max.	<b>Mechanical Properties</b>	
Zirconium	Zr %	0.050 max.	Tensile Strength in Mpa	485 - 550
Copper	Cu %	Balance	Yield Strength in Mpa	220 - 345
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C61300	UNS	USA	Rod, Bar, Tube and Shapes
B100 C61300	ASTM	USA	Plate and Sheet
B111 C61300	ASTM	USA	Tubes
B169 C61300	ASTM	USA	Sheet, Strip and Bar
B171 C61300	ASTM	USA	Plate and Sheet
F467 C61300	ASTM	USA	Bolts, Screws and Studs
SB-111 C61300	ASME	USA	Tubes

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.