



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SB-150 C61900

Specification for Aluminum Bronze Rod, Bar and Shapes

Group - Non-Ferrous Copper Alloy

Sub Group - ASME SB-150 Aluminum Bronze Rod, Bar and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar and Shapes

Chemical Composition			Heat Treatment	
Aluminium	Al %	8.500 - 10.000	As Drawn or Stress Relieving or Hot Rolled	
Iron	Fe %	3.000 - 4.500		
Lead	Pb %	0.020 max.		
Tin	Sn %	0.600 max.		
Zinc	Zn %	0.800 max.		
Cu + Ag	Cu% + Ag%	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 515 - 620 Yield Strength in Mpa 205 - 345 Elongation in % 15 - 25 Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C61900	UNS	USA	Rod, Bar, Tube and Shapes
B124 C61900	ASTM	USA	Rod, Bar and Shapes
B150 C61900	ASTM	USA	Rod, Bar and Shapes
B283 C61900	ASTM	USA	Forging
SB-283 C61900	ASME	USA	Forging
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS