



Material - ASME SB-150 C64210

Standard Specification for Alumium Bronze Rod, Bar and Shapes

Group - Non-Ferrous Copper Alloy

Sub Group - ASME SB-150 Alumium Bronze Rod, Bar and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar and Shape

Chemical Composition			Heat Treatment	
Aluminium	Al %	6.300 - 7.000		
Arsenic	As %	0.150 max.		
Iron	Fe %	0.300 max.		
Manganese	Mn %	0.100 max.	As Drawn or Stress Relieving or Hot Rolled	
Ni + Co	Ni% + Co%	0.250 max.		
Lead	Pb %	0.050 max.		
Silicon	Si %	1.500 - 2.000		
Tin	Sn %	0.200 max.		-
Zinc	Zn %	0.500 max.	Mechanical Properties	
Cu + Ag	Cu% + Ag%	Balance	Tensile Strength in Mpa	485 - 620
-	-		Yield Strength in Mpa	170 - 310
-	-	-	Elongation in %	9 - 15
-	-	-	Reduction of Area in %	
-	-	-	Hardness in HRB	65 - 100
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
C64210	UNS	USA	Rod, Bar, Tube and Shapes	
B124 C64210	ASTM	USA	Rod, Bar and Shape	
B150 C64210	ASTM	USA	Rod, Bar and Shape	
B283 C64210	ASTM	USA	Forging	
SB-283 C64210	ASME	USA	Forging	
-	-	-	1	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.