



Material - ASME SB-151 C75700

Standard Specification for Copper-Nickel-Zinc Alloy (Nickel Silver) and Copper-Nickel Rod and Bar

Group - Non-Ferrous Copper Alloy

Sub Group - ASME SB-151 Copper-Nickel-Zinc Alloy (Nickel Silver) and Copper-Nickel Rod and Bar Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Rod and Bar

Chemical Composition			Heat Treatment	
Iron	Fe %	0.250 max.		
Manganese	Mn %	0.500 max.		
Ni + Co	Ni% + Co%	11.000 - 13.000		
Lead	Pb %	0.050 max.	Normalizing or Annealing or Tempering	ng or Tempering
Cu + Ag	Cu% + Ag%	63.500 - 66.500		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	/ -	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	485 - 760
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-		Hardness in BHN	
-	-	-	Impa <mark>ct in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
CuNi10Zn27	IS	India	Rod and Bar	
B122 C75200	ASTM	USA	Plate, Sheet, Strip and Rolled Bar	
B151 C75200	ASTM	USA	Rod and Bar	
C78400	UNS	USA	Rod and Bar	
B206 C75700	ASTM	USA	Wire	
C75700	UNS	USA	Rod and Bar	
CuNi12Zn29	ISO	International	Plate, Sheet and Strip	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.