



## Material - ASME SB-163 N06600

### Standard Specification for Seamless Nickel and Nickel Alloy Condenser and Heat-Exchanger Tubes

Group - Non-Ferrous Nickel Alloys

Sub Group - ASME SB-163 N06600 Seamless Nickel and Nickel Alloy Condenser and Heat-Exchanger Tube

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Copper	Cu %	0.500 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	14.000 - 17.000		
Iron	Fe %	6.000 - 10.000		
Nickel	Ni %	72.000 min.		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	552 - 758
-	-	-	Yield Strength in Mpa	241 - 448
-	-	-	Elongation in %	4 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	19 - 98
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 163 N06600	ASTM	USA	Tube
B 166 N06600	ASTM	USA	Rod, Bar and Wire
B 167 N06600	ASTM	USA	Pipe and Tube
B 168 N06600	ASTM	USA	Plate, Sheet and Strip
B 472 N06600	ASTM	USA	Bar
NiCr15Fe8	ISO	International	Plate, Sheet and Strip
NW6600	JIS	Japan	Plate, Sheet and Strip

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.