



## Material - ASME SB-283 C14700

## Standard Specification for Copper and Copper-Alloy Die Forgings

**Group - Non-Ferrous Copper Alloy** 

Sub Group - ASME SB-283 Copper and Copper-Alloy Die Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry - Forging** 

Chemical Composition			Heat Treatment	
Phosphorus	P %	0.002 - 0.005		
Sulphur	S %	0.200 - 0.500	Normalizing or Annealing or Tempering	
Copper	Cu %	99.90 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	154.500 - 698.200
-	-	-	Yield Strength in Mpa	55 - 367
-	-	-	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRB	40 min.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
C14700	UNS	USA	Rod, Bar, Tube and Shapes	
B224 C14700	ASTM	USA	Casting	
B283 C14700	ASTM	USA	Forging	
B301 C14700	ASTM	USA	Rod, Bar, Wire and Shapes	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.