

Material - ASME SB-283 C37700

Standard Specification for Copper and Copper-Alloy Forgings

Group - Non-Ferrous Copper Alloy

Sub Group - ASME SB-283 Copper and Copper-Alloy Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Forging

Chemical Composition			Heat Treatment	
Iron	Fe %	0.300 max.		
Lead	Pb %	1.500 - 2.500		
Copper	Cu %	58.000 - 61.000		
Zinc	Zn %	Balance	Normalizing or Annealing or Tempering	ng or Tempering
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	317 - 345
-	-	-	Yield Strength in Mpa	103 - 124
-	-	-	Elongation in %	25 - 30
-	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in BH</mark> N	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
B981 C37700	ASTM	USA	Rod, Bar, Wire and Shapes	
CuZn39Pb2	UNI	Italy	Plate, Sheet and Strip	
CW612N	UNI	Italy	Forging	
CW612N	ONORM	Australia	Forging	
B283 C37700	ASTM	USA	Forging	
CA377	SAE	USA	Forging	
C37700	UNS	USA	Rod, Bar, Tube and Shapes	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS