



Material - ASME SB-435 N06230

Standard Specification for Nickel and Nickel-Related Alloys Plate, Sheet and Strip

Group - Non-Ferrous Nickel Alloys

Sub Group - ASME SB-435 N06230 Nickel and Nickel-Related Alloys Plate, Sheet and Strip Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Sheet, Strip and Plate

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|--------------------------------------|----------|
| Carbon | C % | 0.005 - 0.150 | | |
| Silicon | Si % | 0.250 - 0.750 | | |
| Manganese | Mn % | 0.300 - 1.000 | As-Cast or Annealing or Age Hardning | |
| Chromium | Cr % | 20.000 - 24.000 | | |
| Cobalt | Co % | 5.000 max. | | |
| Molybdenum | Mo % | 1.000 - 3.000 | | |
| Sulphur | S % | 0.015 max. | | |
| Phosphorus | P % | 0.030 max. | | • |
| Aluminium | Al % | 0.500 max. | Mechanical Properties | |
| Iron | Fe % | 3.000 max. | Tensile Strength in Mpa | 760 min. |
| Boron | В % | 0.015 max. | Yield Strength in Mpa | 310 min. |
| Lanthanum | La % | 0.005 - 0.050 | Elongation in % | 40 min. |
| Tungsten | W % | 13.000 - 15.000 | Reduction of Area in % | - |
| Nickel | Ni % | Balance | Hardness in BHN | - |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | |
|-----------------------|----------|---------|--------------------------------|--|
| Material | Standard | Country | Grade Belong to the Industry | |
| UNS N06230 | UNS | USA | Sheet, Strip and Plate | |
| INCONEL alloy N06230 | Gravity | India | Sheet, Strip and Plate | |
| B472 N06230 | ASTM | USA | Billets and Bars for Reforging | |
| B435 N06230 | ASTM | USA | Plate, Sheet and Strip | |
| B564 N06230 | ASTM | USA | Forging | |
| SB-564 N06230 | ASME | USA | Forging | |
| SB-572 N06230 | ASME | USA | Sheet, Strip and Plate | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.