



Material - ASME SB-505 C86300

Standard Specification for Copper Alloy Continuous Casting

Group - Non-Ferrous Copper Alloy

Sub Group - ASME SB-505 Copper Alloy Continuous Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	5.000 - 7.500	As-Cast	
Iron	Fe %	2.000 - 4.000		
Manganese	Mn %	2.500 - 5.000		
Ni + Co	Ni% + Co%	1.000 max.		
Lead	Pb %	0.200 max.		
Tin	Sn %	0.200 max.		
Zinc	Zn %	22.000 - 28.000		
Copper	Cu %	60.000 - 66.000		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 758 min. Yield Strength in Mpa 427 min. Elongation in % 14 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C86300	UNS	USA	Rod, Bar, Tube and Shapes
B271 C86300	ASTM	USA	Casting
B30 C86300	ASTM	USA	Ingot and Casting
CA863	SAE	USA	Casting
SAE 430B	SAE	USA	Casting
SB-584 C86300	ASME	USA	Casting
C86300	AS	Australia	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.