



## Material - ASME SB-584 C94300

### Standard Specification for Copper Alloy Sand Casting for General Applications

Group - Non-Ferrous Copper Alloy

Sub Group - ASME SB-584 Copper Alloy Sand Casting for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.	As-Cast	
Boron	B %	0.001 max.		
Iron	Fe %	0.150 max.		
Magnesium	Mg %	0.005 - 0.150		
Niobium	Nb %	0.100 - 0.300		
Ni + Cu	Ni % + Cu %	1.000 max.		
Phosphorus	P %	0.050 max.		
Lead	Pb %	23.000 - 27.000		
Sulphur	S %	0.080 max.		
Antimony	Sb %	0.800 max.		
Silicon	Si %	0.005 max.		
Tin	Sn %	4.500 - 6.000		
Tin	Sn %	0.010 max.		
Zinc	Zn %	0.800 max.		
Copper	Cu %	67.000 - 72.000		
			Mechanical Properties	
			Tensile Strength in Mpa	165 min.
			Yield Strength in Mpa	-
			Elongation in %	10 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C94300	UNS	USA	Rod, Bar, Tube and Shapes
B144-3E	ASTM	USA	Casting
B30 C94300	ASTM	USA	Ingot and Casting
B505 C94300	ASTM	USA	Casting
C94300	SAE	USA	Casting
CA943	SAE	USA	Casting
SB-505 C94300	ASME	USA	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.