



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SB-619 N06007

Standard Specification for Nickel and Nickel-Cobalt Alloy Pipe

Group - Non-Ferrous Nickel Alloys

Sub Group - ASME SB-619 N06007 Nickel and Nickel-Cobalt Alloy Pipe

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 - 2.000		
Chromium	Cr %	21.000 - 23.500		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	5.500 - 7.500		
Phosphorus	P %	0.040 max.		
Cobalt	Co %	2.500 max.		
Iron	Fe %	18.000 - 21.000		
Copper	Cu %	1.500 - 2.500		
Tungsten	W %	1.000 max.	Mechanical Properties	
Nb + Ta	Nb% + Ta%	1.750 - 2.500	Tensile Strength in Mpa	621 min.
Nickel	Ni %	Balance	Yield Strength in Mpa	241 min.
-	-	-	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 581 N06007	ASTM	USA	Rod
SB-581 N06007	ASME	USA	Rod
B 582 N06007	ASTM	USA	Plate, Sheet and Strip
B 622 N06007	ASTM	USA	Pipe and Tube
B 626 N06007	ASTM	USA	Tube
B 619 N06007	ASTM	USA	Pipe
SB-626 N06007	ASME	USA	Tube

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS