



Material - ASME SF-468 Ni400HF

Standard Specification for Nickel-Copper Alloy, Corrosion Resistant Sheet, Strip and Plate Group - Non-Ferrous Nickel Alloys

Sub Group - ASME SF-468 Ni400HF Nickel-Copper Alloy, Corrosion Resistant Sheet, Strip and Plate Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Sheet, Strip and Plate

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.		
Silicon	Si %	0.500 max.		
Manganese	Mn %	2.000 max.	As-Cast or Annealing or Age Hardning	
Iron	Fe %	2.500 max.		
Sulphur	S %	0.024 max.		
Nickel	Ni %	63.000 - 70.000		
Copper	Cu %	Balance		
-	-	-		
-	-	-	Mechanical Properties	
-	/ -		Tensile Strength in Mpa	480 min.
-	-	-	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	60 - 95
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
Monel 400	SAE	USA	Sheet, Strip and Plate	
F467 Ni400	ASTM	USA	Sheet, Strip and Plate	
F468 Ni400HF	ASTM	USA	Sheet, Strip and Plate	
SF467 Ni400	ASME	USA	Sheet, Strip and Plate	
SF-468 Ni400	ASME	USA	Sheet, Strip and Plate	
NCuR	JIS	Japan	Strip	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.