

## Material - ASTM A 494 CZ100

## Standard Specification for Castings, Nickel and Nickel Alloy

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM A 494 CZ100 Castings, Nickel and Nickel Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	1.000 max.		
Silicon	Si %	2.000 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	Р%	0.030 max.	As-Cast or Annealing or Age Hardning	
Sulphur	S %	0.020 max.		
Copper	Cu %	1.250 max.		
Iron	Fe %	3.000 max.		
Nickel	Ni %	95.000 min.		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	345 min.
-	-	-	Yield Strength in Mpa	125 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in BH</mark> N	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A 494 N02100	ASTM	USA	Casting	
N02100	UNS	USA	Casting	
-	-	-	-	
-	-	-		
-	-	-	-	
-	-	-	-	
-	-	-	-	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## ONE STOP SOLUTION FOR METAL PARTS