



Material - ASTM A 494 M35-1

Standard Specification for Castings, Nickel and Nickel Alloy

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM A 494 M35-1 Castings, Nickel and Nickel Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|--------------------------------------|----------|
| Carbon | C % | 0.350 max. | As-Cast or Annealing or Age Hardning | |
| Silicon | Si % | 1.250 max. | | |
| Manganese | Mn % | 1.500 max. | | |
| Phosphorus | P % | 0.030 max. | | |
| Sulphur | S % | 0.020 max. | | |
| Niobium | Nb % | 0.500 max. | | |
| Copper | Cu % | 26.000 - 33.000 | | |
| Iron | Fe % | 3.500 max. | | |
| Nickel | Ni % | Balance | | |
| - | - | - | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | 450 min. |
| - | - | - | Yield Strength in Mpa | 170 min. |
| - | - | - | Elongation in % | 25 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | - |
| - | - | - | Impact in Joule | - |

| Cross Reference Table | | | |
|-----------------------|----------|---------|------------------------------|
| Material | Standard | Country | Grade Belong to the Industry |
| SA-494 M-35-1 | ASME | USA | Casting |
| C-NiCu30 | AFNOR NF | France | Casting |
| NC4135 | AFNOR NF | France | Casting |
| NU30-M | AFNOR NF | France | Casting |
| N04020 | UNS | USA | Casting |
| N24135 | UNS | USA | Casting |
| - | - | - | - |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.