



Material - ASTM A 753 Type 4

Standard Specification for Nickel-Iron Soft Magnetic Alloys

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM A 753 Type 4 Nickel-Iron Soft Magnetic Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Forging, Billet, Hot rolled plate, Strip, Bar and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.800 max.		
Chromium	Cr %	0.300 max.		
Sulphur	S %	0.010 max.		
Molybdenum	Mo %	3.500 - 6.000		
Phosphorus	P %	0.020 max.		
Cobalt	Co %	0.500 max.		
Copper	Cu %	0.300 max.		
Nickel	Ni %	79.000 - 82.000		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	580 - 1100
-	-	-	Yield Strength in Mpa	220 - 1030
-	-	-	Elongation in %	2 - 40
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	78 - 86
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
N14080	UNS	USA	Forging, Billet, Hot rolled plate, Strip, Bar and Wire
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.