

Material - ASTM B 161 N02201

Standard Specification for Nickel Seamless Pipe and Tube

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 161 N02201 Nickel Seamless Pipe and Tube

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.		
Silicon	Si %	0.350 max.		
Manganese	Mn %	0.350 max.	As-Cast or Annealing or Age Hardning	
Copper	Cu %	0.250 max.		r Age Hardning
Sulphur	S %	0.010 max.		
Iron	Fe %	0.400 max.		
Nickel	Ni %	99.000 min.		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	345 - 480
-	-	-	Yield Strength in Mpa	70 min.
-	-	-	Elongation in %	4 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
B 160 N02201	ASTM	USA	Rod and Bar	
B 162 N02201	ASTM	USA	Plate, Sheet, and Strip	
B 163 N02201	ASTM	USA	Tube	
N02201	UNS	USA	Pipe	
SB-160 N02201	ASME	USA	Rod and Bar	
NLCP	JIS	Japan	Plate, Sheet and Strip	
NW2201	JIS	Japan	Plate, Sheet and Strip	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS