



## Material - ASTM B 163 N04400

### Standard Specification for Seamless Nickel and Nickel Alloy Condenser and Heat-Exchanger Tubes

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 163 N04400 Seamless Nickel and Nickel Alloy Condenser and Heat-Exchanger Tubes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	2.000 max.		
Copper	Cu %	28.000 - 34.000		
Sulphur	S %	0.024 max.		
Iron	Fe %	2.500 max.		
Nickel	Ni %	63.000 min.		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa   483 - 621 Yield Strength in Mpa   193 min. Elongation in %   3 min. Reduction of Area in %   - Hardness in HRC   75 - 97 Impact in Joule   -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 127 N04400	ASTM	USA	Plate, Sheet and Strip
SB 163 N04400	ASTM	USA	Tube
N04400	UNS	USA	Tube
Monel 400	SAE	USA	Sheet, Strip and Plate
B 164 N04400	ASTM	USA	Rod, Bar and Wire
NW4400	JIS	Japan	Plate, Sheet and Strip
B 165 N04400	ASTM	USA	Pipe and Tube

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.