

Material - ASTM B 166 N06617

Standard Specification for Nickel-Chromium-Iron Alloys and Nickel-Chromium-Cobalt-Molybdenum Alloy Rod, Bar and Wire

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 166 N06617 Nickel-Chromium-Iron Alloys and Nickel-Chromium-Cobalt-Molybdenum Alloy Rod, Bar and Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Rod, Bar and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.150		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.	As-Cast or Annealing or Age Hardning	
Copper	Cu %	0.500 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	20.000 - 24.000		
Cobalt	Co %	10.000 - 15.000		
Molybdenum	Mo %	8.000 - 10.000		
Iron	Fe %	3.000 max.	Mechanical Properties	
Aluminium	Al %	0.800 - 1.500	Tensile Strength in Mpa	655 min.
Titanium	Ti %	0.600 max.	Yield Strength in Mpa	240 min.
Boron	B %	0.006 max.	Elongation in %	35 min.
Nickel	Ni %	44.500 min.	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
B 167 N06617	ASTM	USA	Pipe and Tube	
B 168 N06617	ASTM	USA	Plate, Sheet and Strip	
B 564 N06617	ASTM	USA	Forging	
B 626 N06617	ASTM	USA	Tube	
B 546 N06617	ASTM	USA	Pipe	
-	-	-	•	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.