

Material - ASTM B 167 N06617

Standard Specification for Nickel-Chromium-Iron Alloys and Nickel-Chromium-Cobalt-Molybdenum Alloy Seamless Pipe and Tube

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 167 N06617 Nickel-Chromium-Iron Alloys and Nickel-Chromium-Cobalt-Molybdenum Alloy Seamless Pipe and Tube

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Pipe and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.150		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Copper	Cu %	0.500 max.	As-Cast or Annealing or Age Hardning	
Sulphur	S %	0.015 max.		
Chromium	Cr %	20.000 - 24.000		
Aluminium	Al %	0.800 - 1.500		
Boron	B %	0.006 max.		
Iron	Fe %	3.000 max.	Mechanical Properties	
Molybdenum	Mo %	8.000 - 10.000	Tensile Strength in Mpa	665 - 760
Cobalt	Co %	10.000 - 15.000	Yield Strength in Mpa	240 min.
Titanium	Ti %	0.600 max.	Elongation in %	35 min.
Nickel	Ni %	44.500 min.	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
B 166 N06617	ASTM	USA	Rod, Bar and Wire	
B 168 N06617	ASTM	USA	Plate, Sheet and Strip	
B 564 N06617	ASTM	USA	Forging	
B 626 N06617	ASTM	USA	Tube	
B 546 N06617	ASTM	USA	Pipe	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.