

Material - ASTM B 168 N06603

Standard Specification for Nickel-Chromium-Iron Alloys and Nickel-Chromium-Cobalt-Molybdenum Alloy Plate, Sheet and Strip

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 168 N06603 Nickel-Chromium-Iron Alloys and Nickel-Chromium-Cobalt-Molybdenum Alloy Plate, Sheet and Strip

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.400		
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.150 max.	As-Cast or Annealing or Age Hardning	
Copper	Cu %	0.500 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	24.000 - 26.000		
Iron	Fe %	8.000 - 11.000		
Phosphorus	P %	0.020 max.		-
Aluminium	Al %	2.400 - 3.000	Mechanical Properties	
Titanium	Ti %	0.100 - 0.250	Tensile Strength in Mpa	650 min.
Zirconium	Zr %	0.010 - 0.100	Yield Strength in Mpa	300 min.
Yttrium	Y %	0.010 - 0.150	Elongation in %	25 min.
Nickel	Ni %	Balance	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
B 163 N06603	ASTM	USA	Tube	
N06603	UNS	USA	Tube	
B 166 N06603	ASTM	USA	Rod, Bar and Wire	
B 167 N06603	ASTM	USA	Pipe and Tube	
B 516 N06603	ASTM	USA	Tube	
B 517 N06603	ASTM	USA	Pipe	
B 564 N06603	ASTM	USA	Forging	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.