



Material - ASTM B 283 C48500

Standard Specification for Copper and Copper-Alloy Die Forgings

Group - Non Ferrous Copper Alloys

Sub Group - ASTM B 283 C48500 Copper and Copper-Alloy Die Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Forging

Chemical Composition			Heat Treatment	
Iron	Fe %	0.100 max.	As Raw or Solution Heat Treated	
Lead	Pb %	1.300 - 2.200		
Tin	Sn %	0.500 - 1.000		
Copper	Cu %	59.000 - 62.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	358 min.
			Yield Strength in Mpa	152 min.
			Elongation in %	25 min.
			Reduction of Area in %	-
			Hardness in HRC	55 min.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuZn36Pb2Sn1	DIN	Germany	Rod
B 21 C48500	ASTM	USA	Rod, Bar and Shape
B 124 C48500	ASTM	USA	Rod, Bar and Shape
SB-283 C48500	ASME	USA	Forging
2.0371	DIN	Germany	Rod
485	AS	Australia	Forging
C48500	AS	Australia	Ingot and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.