



Material - ASTM B 333 N10665

Standard Specification for Nickel-Molybdenum Alloy Plate, Sheet and Strip

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 333 N10665 Nickel-Molybdenum Alloy Plate, Sheet and Strip Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.		
Silicon	Si %	0.100 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.	As-Cast or Annealing or Age Hardning	
Cobalt	Co %	1.000 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	1.000 max.		
Iron	Fe %	2.000 max.		_
Molybdenum	Mo %	26.000 - 30.000	Mechanical Properties	
Nickel	Ni %	Balance	Tensile Strength in Mpa	760 min.
-	-		Yield Strength in Mpa	350 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRB	100 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
B 335 N10665	ASTM	USA	Rod	
B 564 N10665	ASTM	USA	Forging	
B 462 N10665	ASTM	USA	Pipe and Valve	
B 619 N10665	ASTM	USA	Pipe	
B 622 N10665	ASTM	USA	Pipe and Tube	
B 626 N10665	ASTM	USA	Tube	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.