



Material - ASTM B 333 N10675

Standard Specification for Nickel-Molybdenum Alloy Plate, Sheet and Strip

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 333 N10675 Nickel-Molybdenum Alloy Plate, Sheet and Strip Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Plate, Sheet and Strip

| Chemical Composition | | | Chemical Composition | | |
|----------------------|------|-----------------|--------------------------------------|-----------|-------------|
| Carbon | C % | 0.010 max. | Tungsten | W % | 3.000 max. |
| Silicon | Si % | 0.100 max. | Zirconium | Zr % | 0.100 max. |
| Manganese | Mn % | 3.000 max. | Ni + Mo | Ni% + Mo% | 94.000 - |
| Phosphorus | P % | 0.030 max. | Nickel | Ni % | 65.000 min. |
| Cobalt | Co % | 3.000 max. | - | - | - |
| Sulphur | S % | 0.010 max. | Heat Treatment | | |
| Chromium | Cr % | 1.000 - 3.000 | As-Cast or Annealing or Age Hardning | | |
| Iron | Fe % | 1.000 - 3.000 | | | |
| Molybdenum | Mo % | 27.000 - 32.000 | Mechanical Properties | | |
| Vanadium | V % | 0.200 max. | Tensile Strength in Mpa | 760 min. | |
| Aluminium | Al % | 0.500 max. | Yield Strength in Mpa | 350 min. | |
| Niobium | Nb % | 0.200 max. | Elongation in % | 40 min. | |
| Copper | Cu % | 0.200 max. | Reduction of Area in % | - | |
| Tantalum | Ta % | 0.200 max. | Hardness in HRB | 100 max. | |
| Titanium | Ti % | 0.200 max. | Impact i <mark>n Joule</mark> | - | |

| Cross Reference Table | | | | | |
|-----------------------|----------|---------|------------------------------|--|--|
| Material | Standard | Country | Grade Belong to the Industry | | |
| B 335 N10675 | ASTM | USA | Rod | | |
| B 564 N10675 | ASTM | USA | Forging | | |
| B 472 N10675 | ASTM | USA | Bar | | |
| B 619 N10675 | ASTM | USA | Pipe | | |
| B 622 N10675 | ASTM | USA | Pipe and Tube | | |
| B 626 N10675 | ASTM | USA | Tube | | |
| - | - | - | - | | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.