



Material - ASTM B 39

Standard Specification for Nickel

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 39 Nickel Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.005 max.		
Manganese	Mn %	0.005 max.		
Phosphorus	P %	0.005 max.		
Sulphur	S %	0.010 max.		
Cobalt	Co %	0.150 max.		
Copper	Cu %	0.020 max.		
Iron	Fe %	0.020 max.		
Arsenic	As %	0.005 max.		
Lead	Pb %	0.005 max.		
Antimony	Sb %	0.005 max.	Mechanical Properties	
Bismuth	Bi %	0.005 max.	Tensile Strength in Mpa	300 - 450
Tin	Sn %	0.005 max.	Yield Strength in Mpa	-
Zinc	Zn %	0.005 max.	Elongation in %	-
Nickel	Ni %	99.800 min.	Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.