



## **Material - ASTM B 407 N08811**

Standard Specification for Nickel-Iron-Chromium Alloy Seamless Pipe and Tube

**Group - Non-Ferrous Nickel Alloys** 

Sub Group - ASTM B 407 N08811 Nickel-Iron-Chromium Alloy Seamless Pipe and Tube Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Pipe and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 - 0.100		
Chromium	Cr %	19.000 - 23.000		
Silicon	Si %	1.000 max.	As-Cast or Annealing or Age Hardning	
Manganese	Mn %	1.500 max.		
Aluminium	Al %	0.150 - 0.600		
Sulphur	S %	0.015 max.		
Copper	Cu %	0.750 max.		
Titanium	Ti %	0.150 - 0.600		_
Iron	Fe %	39.500 max.	Mechanical Properties	
Al + Ti	Al % + Ti %	0.850 - 1.200	Tensile Strength in Mpa	450 min.
Nickel	Ni %	30.000 - 35.000	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Country Grade Belong to the Industry	
B 163 N08811	ASTM	USA	Tube	
B 408 N08811	ASTM	USA	Rod and Bar	
B 409 N08811	ASTM	USA	Plate, Sheet and Strip	
B 564 N08811	ASTM	USA	Forging	
SB-163 N08811	ASME	USA	Tube	
N08811	UNS	USA	Tube	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.