



Material - ASTM B 408 N08810

Standard Specification for Nickel-Iron-Chromium Alloy Rod and Bar

Group - Non-Ferrous Nickel Alloys

Sub Group - Standard Specification for Nickel-Iron-Chromium Alloy Rod and Bar Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Rod and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.100	As-Cast or Annealing or Age Hardning	
Chromium	Cr %	19.000 - 23.000		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.500 max.		
Aluminium	Al %	0.150 - 0.600		
Sulphur	S %	0.015 max.		
Copper	Cu %	0.750 max.		
Titanium	Ti %	0.150 - 0.600		_
Iron	Fe %	39.500 max.	Mechanical Properties	
Phosphorus	P %	0.045 max.	Tensile Strength in Mpa	450 min.
Nickel	Ni %	30.000 - 35.000	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
B 163 N08810	ASTM	USA	Tube	
B 407 N08810	ASTM	USA	Pipe and Tube	
B 409 N08810	ASTM	USA	Plate, Sheet and Strip	
B 564 N08810	ASTM	USA	Forging	
SB-163 N08810	ASME	USA	Tube	
N08810	UNS	USA	Tube	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.