



Material - ASTM B 446 N06650

Standard Specification for Nickel-Chromium-Molybdenum-Columbium Alloy, Rod and Bar

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 446 N06650 Nickel-Chromium-Molybdenum-Columbium Alloy, Rod and Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Rod and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	19.000 - 21.000		
Sulphur	S %	0.010 max.		
Copper	Cu %	0.300 max.		
Iron	Fe %	12.000 - 16.000		
Molybdenum	Mo %	9.500 - 12.500		
Cobalt	Co %	1.000 max.		
Aluminium	Al %	0.050 - 0.500		
Nb + Ta	Nb% + Ta%	0.050 - 0.500		
Phosphorus	P %	0.020 max.		
Tungsten	W %	0.500 - 2.500		
Nitrogen	N %	0.050 - 0.200		
Nickel	Ni %	Balance		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SB-446 N06650	ASME	USA	Rod and Bar
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.