



## **Material - ASTM B 472 N06600**

## **Standard Specification for Nickel Bar**

**Group - Non-Ferrous Nickel Alloys** 

Sub Group - ASTM B 472 N06600 Nickel Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.		
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Copper	Cu %	0.500 max.	As-Cast or Annealing or Age Hardning	
Sulphur	S %	0.015 max.		
Chromium	Cr %	14.000 - 17.000		
Iron	Fe %	6.000 - 10.000		
Nickel	Ni %	72.000 min.		-
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	550 min.
-	-	-	Yield Strength in Mpa	240 min.
-	-	-	Elongation in %	2 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	30 - 98
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
B 163 N06600	ASTM	USA	Tube	
B 166 N06600	ASTM	USA	Rod, Bar and Wire	
B 167 N06600	ASTM	USA	Pipe and Tube	
SB-163 N06600	ASME	USA	Tube	
B 168 N06600	ASTM	USA	Plate, Sheet and Strip	
NiCr15Fe8	ISO	International	Plate, Sheet and Strip	
NW6600	JIS	Japan	Plate, Sheet and Strip	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.