



Material - ASTM B 472 N08367

Standard Specification for Nickel Alloy Billets and Bars for Reforging

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 472 N08367 Nickel Alloy Billets and Bars for Reforging

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Billet and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Copper	Cu %	0.750 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	20.000 - 22.000		
Phosphorus	P %	0.040 max.		
Molybdenum	Mo %	6.000 - 7.000		
Nitrogen	N %	0.180 - 0.250		
Nickel	Ni %	23.500 - 25.500	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	655 min.
-	-	-	Yield Strength in Mpa	310 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	50 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N08367	ASTM	USA	Forging
B 688 N08367	ASTM	USA	Plate, Sheet and Strip
B 691 N08367	ASTM	USA	Rod, Bar and Wire
B 462 N08367	ASTM	USA	Pipe Flanges, Forged Fittings, and Valve
A 314 N08367	ASTM	USA	Bar and Forging
B 690 N08367	ASTM	USA	Pipe and Tube
B 834 N08367	ASTM	USA	Pipe Flanges, Forged Fittings, and Valve

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.