



Material - ASTM B 564 N06025

Standard Specification for Nickel Alloy Forgings

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 564 Nickel Alloy Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 - 0.250	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.150 max.		
Chromium	Cr %	24.000 - 26.000		
Sulphur	S %	0.010 max.		
Copper	Cu %	0.100 max.		
Aluminium	Al %	1.800 - 2.400		
Titanium	Ti %	0.100 - 0.200		
Phosphorus	P %	0.020 max.		
Iron	Fe %	8.000 - 11.000		
Zirconium	Zr %	0.010 - 0.100	Mechanical Properties Tensile Strength in Mpa 580 min. Yield Strength in Mpa 270 min. Elongation in % 15 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Yttrium	Y %	0.050 - 0.120		
Nickel	Ni %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 163 N06025	ASTM	USA	Tube
B 166 N06025	ASTM	USA	Rod, Bar and Wire
B 167 N06025	ASTM	USA	Pipe and Tube
B 168 N06025	ASTM	USA	Plate, Sheet and Strip
B 516 N06025	ASTM	USA	Tube
B 517 N06025	ASTM	USA	Pipe
B 462 N06025	ASTM	USA	Pipe and Valve

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.