



Material - ASTM B 564 N06210

Standard Specification for Nickel Alloy Forgings

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 564 N06210 Nickel Alloy Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.015 max.		
Silicon	Si %	0.080 max.		
Manganese	Mn %	0.500 max.	As-Cast or Annealing or Age Hardning	
Chromium	Cr %	18.000 - 20.000		
Sulphur	S %	0.020 max.		
Molybdenum	Mo %	18.000 - 20.000		
Phosphorus	Р%	0.020 max.		
Cobalt	Co %	1.000 max.		
Vanadium	V %	0.350 max.	Mechanical Properties	
Tantalum	Та %	1.500 - 2.200	Tensile Strength in Mpa	690 min.
Iron	Fe %	1.000 max.	Yield Strength in Mpa	310 min.
Nickel	Ni %	Balance	Elongation in %	45 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Gr <mark>ade Belong</mark> to the Industry		
B 574 N06210	ASTM	USA	Rod		
B 575 N06210	ASTM	USA	Plate, Sheet and Strip		
B 619 N06210	ASTM	USA	Pipe		
B 622 N06210	ASTM	USA	Pipe and Tube		
B 626 N06210	ASTM	USA	Tube		
-	-		-		
-	-		-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS