

Material - ASTM B 564 N08120

Standard Specification for Nickel Alloy Forgings

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 564 N08120 Nickel Alloy Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Forging

| Chemical Composition | | | Chemical Composition | | |
|----------------------|-----------|-----------------|--------------------------------------|----------|----------|
| Carbon | C % | 0.020 - 0.100 | Nickel | Ni % | 33.000 - |
| Silicon | Si % | 1.000 max. | Iron | Fe % | Balance |
| Manganese | Mn % | 1.500 max. | - | - | - |
| Chromium | Cr % | 23.000 - 27.000 | - | - | - |
| Sulphur | S % | 0.030 max. | - | - | - |
| Copper | Cu % | 0.500 max. | Heat Treatment | | |
| Phosphorus | P % | 0.040 max. | As-Cast or Annealing or Age Hardning | | |
| Aluminium | Al % | 0.400 max. | | | |
| Titanium | Ti % | 0.200 max. | Mechanical Properties | | |
| Nb + Ta | Nb% + Ta% | 0.400 - 0.900 | Tensile Strength in Mpa | 622 | 1 min. |
| Molybdenum | Mo % | 2.500 max. | Yield Strength in Mpa | 276 min. | |
| Tungsten | W % | 2.500 max. | Elongation in % | 30 min. | |
| Cobalt | Co % | 3.000 max. | Reduction of Area in % | - | |
| Nitrogen | N % | 0.150 - 0.300 | Hardness in BHN | - | |
| Boron | В % | 0.010 max. | Impact i <mark>n Joule</mark> | | - |

| Cross Reference Table | | | | | |
|-----------------------|----------|---------|------------------------------|--|--|
| Material | Standard | Country | Grade Belong to the Industry | | |
| B 163 N08120 | ASTM | USA | Tube | | |
| B 407 N08120 | ASTM | USA | Pipe and Tube | | |
| B 408 N08120 | ASTM | USA | Rod and Bar | | |
| B 409 N08120 | ASTM | USA | Plate, Sheet and Strip | | |
| SB-163 N08120 | ASME | USA | Tube | | |
| N08120 | UNS | USA | Forging | | |
| - | - | - | - | | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.