



Material - ASTM B 564 N10242

Standard Specification for Nickel Alloy Forgings

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 564 N10242 Nickel Alloy Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.		
Silicon	Si %	0.800 max.		
Manganese	Mn %	0.800 max.		
Aluminium	Al %	0.500 max.	As-Cast or Annealing or Age Hardning	
Sulphur	S %	0.015 max.		
Chromium	Cr %	7.000 - 9.000		
Molybdenum	Mo %	24.000 - 26.000		
Iron	Fe %	2.000 max.		
Cobalt	Co %	1.000 max.	Mechanical Properties	
Phosphorus	P %	0.030 max.	Tensile Strength in Mpa	725 min.
Boron	В %	0.006 max.	Yield Strength in Mpa	310 min.
Nickel	Ni %	Balance	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-		Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
B 434 N10242	ASTM	USA	Plate, Sheet and Strip	
B 573 N10242	ASTM	USA	Rod	
B 619 N10242	ASTM	USA	Pipe	
B 622 N10242	ASTM	USA	Pipe and Tube	
B 626 N10242	ASTM	USA	Tube	
SB-573 N10242	ASME	USA	Rod	
SB-619 N10242	ASME	USA	Pipe	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.