



Material - ASTM B 564 N10276

Standard Specification for Nickel Alloy Forgings

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 564 N10276 Nickel Alloy Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Forging

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|--------------------------------------|----------|
| Carbon | C % | 0.010 max. | | |
| Silicon | Si % | 0.080 max. | | |
| Manganese | Mn % | 1.000 max. | | |
| Chromium | Cr % | 14.500 - 16.500 | As-Cast or Annealing or Age Hardning | |
| Sulphur | S % | 0.030 max. | | |
| Molybdenum | Mo % | 15.000 - 17.000 | | |
| Phosphorus | Р% | 0.040 max. | | |
| Cobalt | Co % | 2.500 max. | | |
| Iron | Fe % | 4.000 - 7.000 | Mechanical Properties | |
| Tungsten | W % | 3.000 - 4.500 | Tensile Strength in Mpa | 690 min. |
| Vanadium | V % | 0.350 max. | Yield Strength in Mpa | 283 min. |
| Nickel | Ni % | Balance | Elongation in % | 40 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | - |
| - | - | - | Impact in Joule | - |

| Cross Reference Table | | | | | |
|-----------------------|----------|---------|--|--|--|
| Material | Standard | Country | Gr <mark>ade Belong</mark> to the Industry | | |
| B 574 N10276 | ASTM | USA | Rod | | |
| B 575 N10276 | ASTM | USA | Plate, Sheet and Strip | | |
| B 462 N10276 | ASTM | USA | Pipe Flanges, Forged Fittings, and Valve | | |
| B 619 N10276 | ASTM | USA | Ріре | | |
| B 622 N10276 | ASTM | USA | Pipe and Tube | | |
| B 626 N10276 | ASTM | USA | Tube | | |
| N10276 | UNS | USA | Casting | | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS