



Material - ASTM B 574 N06200

Standard Specification for Low-Carbon Nickel-Chromium-Molybdenum, Alloy Rod

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 574 N06200 Low-Carbon Nickel-Chromium-Molybdenum, Alloy Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.080 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	22.000 - 24.000		
Sulphur	S %	0.010 max.		
Molybdenum	Mo %	15.000 - 17.000		
Phosphorus	P %	0.025 max.		
Cobalt	Co %	2.000 max.		
Iron	Fe %	3.000 max.		
Aluminium	Al %	0.500 max.		
Copper	Cu %	1.300 - 1.900	Mechanical Properties	
Nickel	Ni %	Balance	Tensile Strength in Mpa	690 min.
-	-	-	Yield Strength in Mpa	310 min.
-	-	-	Elongation in %	45 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N06200	ASTM	USA	Forging
B 575 N06200	ASTM	USA	Plate, Sheet and Strip
B 462 N06200	ASTM	USA	Pipe Flanges, Forged Fittings and Valve
B 619 N06200	ASTM	USA	Pipe
B 622 N06200	ASTM	USA	Pipe and Tube
B 626 N06200	ASTM	USA	Tube
B 472 N06200	ASTM	USA	Billets and Bars

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.