



Material - ASTM B 575 N06058

Standard Specification for Low-Carbon Nickel-Chromium-Molybdenum, Alloy Plate, Sheet and Strip

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 575 N06058 Low-Carbon Nickel-Chromium-Molybdenum, Alloy Plate, Sheet and Strip

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.100 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	20.000 - 23.000		
Sulphur	S %	0.010 max.		
Molybdenum	Mo %	18.500 - 21.000		
Phosphorus	P %	0.015 max.		
Aluminium	Al %	0.400 max.		
Iron	Fe %	1.500 max.		
Cobalt	Co %	0.300 max.		
Copper	Cu %	0.500 max.		
Tungsten	W %	0.300 max.		
Nitrogen	N %	0.020 - 0.150		
Nickel	Ni %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N06058	ASTM	USA	Forging
B 574 N06058	ASTM	USA	Rod
B 619 N06058	ASTM	USA	Pipe
B 622 N06058	ASTM	USA	Pipe and Tube
B 626 N06058	ASTM	USA	Tube
SB-564 N06058	ASME	USA	Forging
SB-574 N06058	ASME	USA	Rod

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.