



Material - ASTM B 619 N10629

Standard Specification for Nickel and Nickel-Cobalt Alloy Pipe

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 619 N10629 Nickel and Nickel-Cobalt Alloy Pipe

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.050 max.		
Manganese	Mn %	1.500 max.		
Copper	Cu %	0.500 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	0.500 - 1.500		
Phosphorus	P %	0.040 max.		
Molybdenum	Mo %	26.000 - 30.000		
Aluminium	Al %	0.100 - 0.500		
Cobalt	Co %	2.500 max.	Mechanical Properties	
Iron	Fe %	1.000 - 6.000	Tensile Strength in Mpa	760 min.
Nickel	Ni %	Balance	Yield Strength in Mpa	350 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 333 N10629	ASTM	USA	Plate, Sheet and Strip
B 335 N10629	ASTM	USA	Rod
B 564 N10629	ASTM	USA	Forging
B 472 N10629	ASTM	USA	Bar
B 622 N10629	ASTM	USA	Pipe and Tube
B 626 N10629	ASTM	USA	Tube
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.