



Material - ASTM B 622 N06200

Standard Specification for Seamless Nickel and Nickel-Cobalt Alloy Pipe and Tube

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 622 N06200 Seamless Nickel and Nickel-Cobalt Alloy Pipe and Tube Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Pipe and Tube

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|--------------------------------------|-----------------|
| Carbon | C % | 0.010 max. | | |
| Silicon | Si % | 0.080 max. | | |
| Manganese | Mn % | 0.500 max. | As-Cast or Annealing or Age Hardning | |
| Chromium | Cr % | 22.000 - 24.000 | | or Age Hardning |
| Sulphur | S % | 0.010 max. | | |
| Molybdenum | Mo % | 15.000 - 17.000 | | |
| Phosphorus | P % | 0.025 max. | | |
| Cobalt | Co % | 2.000 max. | | _ |
| Copper | Cu % | 1.300 - 1.900 | Mechanical Properties | |
| Aluminium | Al % | 0.500 max. | Tensile Strength in Mpa | 690 min. |
| Iron | Fe % | 3.000 max. | Yield Strength in Mpa | 310 min. |
| Nickel | Ni % | Balance | Elongation in % | 45 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardn <mark>ess in BH</mark> N | - |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | |
|-----------------------|----------|---------|---|--|
| Material | Standard | Country | Grade Belong to the Industry | |
| B 564 N06200 | ASTM | USA | Forging | |
| B 574 N06200 | ASTM | USA | Rod | |
| B 575 N06200 | ASTM | USA | Plate, Sheet and Strip | |
| B 462 N06200 | ASTM | USA | Pipe Flanges, Forged Fittings and Valve | |
| B 619 N06200 | ASTM | USA | Pipe | |
| B 626 N06200 | ASTM | USA | Tube | |
| B 472 N06200 | ASTM | USA | Billets and Bars | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.