



Material - ASTM B 622 N06210

Standard Specification for Seamless Nickel and Nickel-Cobalt Alloy Pipe and Tube

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 622 N06210 Seamless Nickel and Nickel-Cobalt Alloy Pipe and Tube Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Pipe and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.015 max.		
Silicon	Si %	0.080 max.		
Manganese	Mn %	0.500 max.		
Chromium	Cr %	18.000 - 20.000	As-Cast or Annealing or Age Hardning	or Age Hardning
Sulphur	S %	0.020 max.		
Molybdenum	Mo %	18.000 - 20.000		
Phosphorus	P %	0.020 max.		
Cobalt	Co %	1.000 max.		
Iron	Fe %	1.000 max.	Mechanical Properties	
Vanadium	V %	0.350 max.	Tensile Strength in Mpa	690 min.
Tantalum	Ta %	1.500 - 2.200	Yield Strength in Mpa	310 min.
Nickel	Ni %	Balance	Elongation in %	45 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Gr <mark>ade Belong</mark> to the Industry		
B 564 N06210	ASTM	USA	Forging		
B 574 N06210	ASTM	USA	Rod		
B 575 N06210	ASTM	USA	Plate, Sheet and Strip		
B 619 N06210	ASTM	USA	Pipe		
B 626 N06210	ASTM	USA	Tube		
-	-		-		
-	-		-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.