

Material - ASTM B 677 N08926

Standard Specification for Nickel-Iron-Chromium-Molybdenum and Iron-Nickel-Chromium-Molybdenum-Copper Seamless Pipe and Tube

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 677 N08926 Nickel-Iron-Chromium-Molybdenum and Iron-Nickel-Chromium-Molybdenum-Copper Seamless Pipe and Tube

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Pipe and Tube

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|--------------------------------------|----------|
| Carbon | C % | 0.020 max. | | |
| Silicon | Si % | 0.500 max. | | |
| Manganese | Mn % | 2.000 max. | | |
| Chromium | Cr % | 19.000 - 21.000 | As-Cast or Annealing or Age Hardning | |
| Sulphur | S % | 0.010 max. | | |
| Molybdenum | Mo % | 6.000 - 7.000 | | |
| Phosphorus | P % | 0.030 max. | | |
| Copper | Cu % | 0.500 - 1.500 | | _ |
| Nitrogen | N % | 0.150 - 0.250 | Mechanical Properties | |
| Nickel | Ni % | 24.000 - 26.000 | Tensile Strength in Mpa | 650 min. |
| Iron | Fe % | Balance | Yield Strength in Mpa | 295 min. |
| - | - | - | Elongation in % | 35 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | - |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | | |
|-----------------------|----------|---------|--|--|--|
| Material | Standard | Country | Grade Belong to the Industry | | |
| B 649 N08926 | ASTM | USA | Bar and Wire | | |
| A 182 F1925N | ASTM | USA | Pipe Flanges, Forged Fittings and Valves | | |
| B 472 N08926 | ASTM | USA | Billets and Bars | | |
| B 625 N08926 | ASTM | USA | Plate, Sheet and Strip | | |
| B 673 N08926 | ASTM | USA | Pipe | | |
| B 674 N08926 | ASTM | USA | Tube | | |
| SB-625 N08926 | ASME | USA | Plate, Sheet and Strip | | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.