



Material - ASTM B 688 N08366

Standard Specification for Chromium-Nickel-Molybdenum-Iron Plate, Sheet and Strip

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 688 N08366 Chromium-Nickel-Molybdenum-Iron Plate, Sheet and Strip Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.035 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Chromium	Cr %	20.000 - 22.000	As-Cast or Annealing or Age Hardning	or Age Hardning
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	6.000 - 7.000		
Phosphorus	P %	0.040 max.		
Nickel	Ni %	23.500 - 25.500		
Iron	Fe %	Balance	Mechanical Properties	
-	-		Tensile Strength in Mpa	515 min.
-	-	-	Yield Strength in Mpa	240 min.
-	-	-	Elongation in %	30 min.
-	-		Reduction of Area in %	-
-	-	-	Hardness in BHN	212 max.
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
B 691 N08366	ASTM	USA	Rod, Bar and Wire	
B 690 N08366	ASTM	USA	Pipe and Tube	
SB-690 N08366	ASME	USA	Pipe and Tube	
SB-691 N08366	ASME	USA	Rod, Bar and Wire	
SB-688 N08366	ASME	USA	Plate, Sheet and Strip	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.