



## **Material - ASTM B 704 N06219**

## **Standard Specification for Nickel Alloy Tubes**

**Group - Non-Ferrous Nickel Alloys** 

Sub Group - ASTM B 704 N06219 Nickel Alloy Tubes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.		
Silicon	Si %	0.700 - 1.100		
Manganese	Mn %	0.500 max.	As-Cast or Annealing or Age Hardning	
Copper	Cu %	0.500 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	18.000 - 22.000		
Aluminium	Al %	0.500 max.		
Molybdenum	Mo %	7.000 - 9.000		
Iron	Fe %	2.000 - 4.000	Mechanical Properties	
Phosphorus	P %	0.020 max.	Tensile Strength in Mpa	660 min.
Titanium	Ti %	0.500 max.	Yield Strength in Mpa	270 min.
Cobalt	Co %	1.000 max.	Elongation in %	30 min.
Nickel	Ni %	Balance	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
B 446 N06219	ASTM	USA	Rod and Bar	
B 443 N06219	ASTM	USA	Plate, Sheet and Strip	
B 444 N06219	ASTM	USA	Pipe and Tube	
B 564 N06219	ASTM	USA	Forging	
B 705 N06219	ASTM	USA	Pipe	
SB-443 N06219	ASME	USA	Plate, Sheet and Strip	
SB-444 N06219	ASME	USA	Pipe and Tube	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.