



Material - ASTM B 705 N06219

Standard Specification for Nickel Alloy Pipe

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 705 N06219 Nickel Alloy Pipe

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.700 - 1.100		
Manganese	Mn %	0.500 max.		
Copper	Cu %	0.500 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	18.000 - 22.000		
Aluminium	Al %	0.500 max.		
Molybdenum	Mo %	7.000 - 9.000		
Iron	Fe %	2.000 - 4.000		
Phosphorus	P %	0.020 max.		
Titanium	Ti %	0.500 max.	Mechanical Properties	
Cobalt	Co %	1.000 max.	Tensile Strength in Mpa	660 min.
Nickel	Ni %	Balance	Yield Strength in Mpa	270 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 446 N06219	ASTM	USA	Rod and Bar
B 443 N06219	ASTM	USA	Plate, Sheet and Strip
B 444 N06219	ASTM	USA	Pipe and Tube
B 564 N06219	ASTM	USA	Forging
B 704 N06219	ASTM	USA	Tube
SB-443 N06219	ASME	USA	Plate, Sheet and Strip
SB-444 N06219	ASME	USA	Pipe and Tube

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.