



Material - ASTM B 710 N08330

Standard Specification for Nickel-Iron-Chromium-Silicon Alloy Pipe

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 710 N08330 Nickel-Iron-Chromium-Silicon Alloy Pipe

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe

Chemical Composition			Heat Treatment			
Carbon	C %	0.080 max.	As-Cast or Annealing or Age Hardning			
Silicon	Si %	0.750 - 1.500				
Manganese	Mn %	2.000 max.				
Chromium	Cr %	17.000 - 20.000				
Sulphur	S %	0.030 max.				
Copper	Cu %	1.000 max.				
Phosphorus	P %	0.030 max.				
Nickel	Ni %	34.000 - 37.000				
Lead	Pb %	0.005 max.				
Tin	Sn %	0.025 max.				
Iron	Fe %	Balance	<th colspan="2">Mechanical Properties</th>		Mechanical Properties	
-	-	-	Tensile Strength in Mpa	483 min.		
-	-	-	Yield Strength in Mpa	207 min.		
-	-	-	Elongation in %	30 min.		
-	-	-	Reduction of Area in %	-		
-	-	-	Hardness in HRC	70 - 90		
-	-	-	Impact in Joule	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 511 N08330	ASTM	USA	Bar and Shape
B 512 N08330	ASTM	USA	Billets and Bar
B 535 N08330	ASTM	USA	Pipe and Tube
B 536 N08330	ASTM	USA	Plate, Sheet and Strip
B 739 N08330	ASTM	USA	Tube
SB-511 N08330	ASME	USA	Bar and Shape
SB-535 N08330	ASME	USA	Pipe and Tube

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.