



Material - ASTM B 725 N04400

Standard Specification for Nickel and Nickel Copper Alloy Pipe

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 725 N04400 Nickel and Nickel Copper Alloy Pipe

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe

| Chemical Composition | | | Heat Treatment | |
|----------------------|------------|-----------------|--------------------------------------|-----------------|
| Carbon | C % | 0.300 max. | | |
| Silicon | Si % | 0.500 max. | | |
| Manganese | Mn % | 2.000 max. | | |
| Copper | Cu % | 28.000 - 34.000 | As-Cast or Annealing or Age Hardning | or Age Hardning |
| Sulphur | S % | 0.024 max. | | |
| Iron | Fe % | 2.500 max. | | |
| Nickel | Ni % | 63.000 min. | | |
| - | - | - | | |
| - | - | - | Mechanical Properties | |
| - | / - | | Tensile Strength in Mpa | 480 min. |
| - | - | - | Yield Strength in Mpa | 170 min. |
| - | - | - | Elongation in % | 15 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | - |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | |
|-----------------------|----------|--------------------------------------|------------------------|--|
| Material | Standard | Country Grade Belong to the Industry | | |
| B 164 N04400 | ASTM | USA | Rod, Bar and Wire | |
| B 165 N04400 | ASTM | USA | Pipe and Tube | |
| B 564 N04400 | ASTM | USA | Forging | |
| B 127 N04400 | ASTM | USA | Plate, Sheet and Strip | |
| B 163 N04400 | ASTM | USA | Tube | |
| SB-163 N04400 | ASME | USA | Tube | |
| SB-165 N04400 | ASME | USA | Pipe and Tube | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.