



Material - ASTM B 730 N02201

Standard Specification for Nickel and Nickel Copper Alloy Tube

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 730 N02201 Nickel and Nickel Copper Alloy Tube

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.350 max.		
Manganese	Mn %	0.350 max.		
Copper	Cu %	0.250 max.		
Sulphur	S %	0.010 max.		
Iron	Fe %	0.400 max.		
Nickel	Ni %	Balance		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	345 min.
-	-	-	Yield Strength in Mpa	70 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 725 N02201	ASTM	USA	Pipe
N02201	UNS	USA	Pipe
B 160 N02201	ASTM	USA	Rod and Bar
B 161 N02201	ASTM	USA	Pipe and Tube
B 162 N02201	ASTM	USA	Plate, Sheet and Strip
B 163 N02201	ASTM	USA	Tube
SB-160 N02201	ASME	USA	Rod and Bar

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.